

Lotrène® FD0270

LOW DENSITY POLYETHYLENE
(LDPE)

DESCRIPTION

Lotrène® FD0270 is an additive free grade mainly recommended for the extrusion of thin film for light and medium duty applications.

PROPERTIES

The molecular structure of Lotrène® FD0270 makes it possible to produce very thin, clear and glossy films.

PROCESSING

Lotrène® FD0270 can be easily processed on all types of extruders to make blown or cast films. The melt temperature is suggested to be in the range of 140-150 °C. The best properties of the blown film are achieved at blow up ratios between 2:1 and 3:1. The recommended thickness range is from 20 µm to 100 µm.

| POLYMER PROPERTIES | VALUE | UNIT | TEST METHOD |
|---------------------------|-------|-------------------|-------------|
| Melt flow index | 2.4 | g/10 min. | ASTM D-1238 |
| Density @ 23 °C | 0.923 | g/cm ³ | ASTM D-792 |
| Crystalline melting Point | 112 | °C | ASTM E-794 |
| Vicat softening point | 96 | °C | ASTM D-1525 |

| FILM PROPERTIES | VALUE | UNIT | TEST METHOD |
|----------------------------------|---------|------|-----------------|
| Tensile strength @ yield MD/ TD | 12/12 | MPa | ASTM D-882 |
| Tensile strength @ break MD/ TD | 28/24 | MPa | ASTM D-882 |
| Elongation @ break MD/ TD | 430/660 | % | ASTM D-882 |
| Tear resistance MD/ TD | 90/70 | N/mm | ASTM D-1922 |
| Puncture force | 50 | N | Internal Method |
| Impact strength, F ₅₀ | 85 | g | ASTM D-1709 |
| Coefficient of friction | 1.2 | | ASTM D-1894 |
| Haze | 5.5 | % | ASTM D-1003 |
| Gloss @ 45° | 73 | | ASTM D-2457 |

Film properties stated above have been obtained using 40 µm blown films laboratory test specimens produced under following conditions: 45 mm screw with L/D = 30, die diameter 120 mm, die gap 1.56 mm, BUR 2:5:1

APPLICATIONS

- High clarity bags
- Thin shrink film
- Lamination film
- Foamed products

HANDLING & STORAGE

Polyethylene products should be stored in their original packaging or in clean appropriate silos. The products should be stored in a dry and well-ventilated area and should not be exposed to direct sunlight and/or heat in any form since this may adversely affect their properties.

As a general rule, our products should not be stored for more than three months from receipt date.

SAFETY

Under normal conditions Lotrène® products do not present a toxic hazard through skin contact or inhalation. For detailed information please refer to the Safety Data Sheet.

FOOD CONTACT & REACH

Lotrène® polyethylene products manufactured by Qatar Petrochemical Company (QAPCO) Q.P.J.S.C. comply with US, EU and other food contact legislations. Limitations may apply. Please contact your QatarEnergy marketing representative for detailed compliance certificates.

All QAPCO Lotrène® products are complying with REACH Regulation 1907/2006/EC. The aims of this regulation are to improve the protection of human health and the environment through better and earlier identification of the intrinsic properties of chemical substances.

NOT SUITABLE FOR PHARMACEUTICAL OR MEDICAL APPLICATIONS

Lotrène® products are not suitable for pharmaceutical or medical applications.

TECHNICAL DISCLAIMER

Before using this product, the user is advised and cautioned to make its own determination and assessment of the safety and suitability of the product for the specific use in question and is further advised against relying on the information contained herein as it may relate to any specific use or application. It is the ultimate responsibility of the user to ensure that the product is suited for and the information is applicable to the user's specific application. Any data included herein is based upon analysis of representative samples in a laboratory environment and not the actual product shipped. The values indicated in this datasheet should not be used for specification purposes.

The information in this document relates only to the named product or material when not in combination with any other product or materials. The information is based on data believed to be reliable on the date compiled. We do not make, and expressly disclaims, all warranties, including warranties of merchantability or fitness for a particular purpose, regardless of whether oral or written, express or implied, or allegedly arising from any usage of any trade or from any course of dealing in connection with the use of the information contained herein or the product itself.

The user expressly assumes all risk and liability, whether based in contact, tort or otherwise, in connection with the use of the information contained herein or the product itself. Further, information contained herein is given without reference to any intellectual property issues for which any liability for infringement or alleged infringement are fully disclaimed, as well as any international laws which may be encountered in the use thereof. Such questions should be investigated by the user. Trademarks may not be used in any manner other than expressly authorized in a written agreement and no trademark or license rights of any kind are granted hereunder, by implication or otherwise.